

Tel: 01978 661247 Fax: 01978 660373 FREEPHONE: 0800 018 1247
E-mail: sales@lyanpackaging.co.uk Website: www.lyanpackaging.co.uk

Recycled Content Of Paper

The following table identifies the recycled content of each type of paper used in the manufacture of corrugated fibreboard.

Paper	Commonly Known As	Recycled Content
White Test	WT	100%
Test Two	TL2 / G	100%
Test Three	T	100%
Waste Base Fluting	WB	100%
Brown Kraft	K	25-30%
White Kraft	WK	0%
Semi Chemical Fluting	SC	30-35%
Mottle Test	MT	100%
Mottle Kraft	MK	30%
Grey Chip	CHIP	100%
Kemi Lite	KEM / X	0%
Clay Coat	CW	0%

The SPA figure for an average across the entire industry (i.e. all board grades combined) is 84%